






















TECHNICAL CHARACTERISTICS

ambra Multi-Layer Long-lasting multi-layer floor (Multi-Layer) according to EN 14085 for glueless installation			wineo	
	ambra wood Multi-Layer	ambra stone Multi-Layer		
Format	1200 x 212 mm	591 x 287 mm		
Product thickness	9 mm	9 mm		
Planks, tiles / m² per box	8 / 2.04 m ²	9 / 1.53 m ²		
Boxes / m² per pallet	48 / 97.92 m ²	60 / 91.80 m ²		
Guarantee	15 years – Guarantee for private use according to Windmüller warranty conditions – www.wineo.de			
Classification			Product composition	
	Utilization class 23 Heavy-duty use in the domestic area EN ISO 10874	Corridors, living rooms, kitchens, home offices	1	Surface sealing
	Utilization class 31 Medium use in the commercial sector EN ISO 10874	Hotel rooms, small offices	2	Wear layer Thickness 0.3 mm
	Wear resistance EN 660-2	Group T	3	Decor film Surface texture - various embossings
	Reaction to fire EN 13501-1	B _{fl} - s1	4	Core board Aqua-Protect®
	Anti slip category DIN 51130	R 9		Profile connection LocTec® technology 
	Slip resistance EN 13893	μ ≥ 0.30 - DS		Insulation mat Sound-Protect Eco
	Anti-static properties EN 1815	≤ 2 kV		
	Staining and chemical resistance EN ISO 26987	Good resistance according to the concentration and residence time	Certifications	
	Light fastness EN ISO 105-B02	≥ 6	   	
	Residual indentation EN ISO 24343-1	~ 0.02 mm		
	Castor chair test EN 425 / ISO 4918	Type W – no visible change		
	Thermal resistance EN 12667	~ 0.06 (m ² K)/W		
	Impact sound reduction EN ISO 16251-1	up to 14 dB		
	Formaldehyde emission EN 717-1	E1		
	Disposal	<u>Private:</u> Possible with normal domestic refuse <u>Commercial:</u> Refuse-key-no. AVV 170203		

Relevant information:

- Underfloor heating: In conjunction with suitable underlay material, suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 27° C.
- Cleaning and care: see separate cleaning & care instruction.
- Technical subjects can be changed by windmüller flooring products WFP GmbH.